

## Sepahan Slack Wax H-12

<b>Slack Wax H-12</b>		
<b>Test</b>	<b>ASTM</b>	<b>Spec</b>
Kin. Vis @ 100°C	D-445	5.5-7.5
Oil cont. % wt	D-721	8-12
Density @ 15.6°C (g/cm <sup>3</sup> ) typical	D-4052	0.81-0.84
Flash Point (°C) (min)	D-92	240
Color @ 70°C (max)	D-1500	3
Congeaing Point (°C) typical	D-938	59