

SEPAHAN PARAFFIN WAX

	Test	Method	Unit	Results
1	Kinematic Viscosity @100°C	ASTM D7042	C.St	5.5 -7.5
2	Density @ 15.6 °C	ASTM D4052	gr/cm ³	0.81-0.84
3	Flash point "Cleveland Open Cup" (Min)	ASTM D92	°C	240
4	Color @ 70°C (Max)	ASTM D1500	---	3.0
6	Oil Content	ASTM D721	Wt%	2 - 5
7	Congealing Point	ASTM D938	°C	63